

Serial No.: 09/45,107  
Docket No.: AD-6430 US CIP

Page 2

optionally at least one barrier layer, the blown film  
[made] obtained by a [rapid] film fabrication process wherein  
the process time is 12 seconds or less, and wherein the  
adhesive composition[,] comprises:

- a) a polyethylene selected from the group consisting of conventional-HDPE, conventional-MDPE, conventional-LLDPE, conventional-VLDPE, LDPE, and a blend of any of these five,
  - b) from 5 to 35 weight percent, based on the total weight of a) plus b) plus c), of an acid-grafted substantially linear polyethylene, c) optionally up to 30 weight percent of a hydrocarbon elastomer,
- the acid grafting agent being an unsaturated carboxylic acid or its derivative, and the level of grafting being such that the total amount of grafting agent in the total composition a) plus b) plus c) is from 0.01 to 3 weight percent.

After amendment, Claim 15 should read as follows:

Sub B1  
AL

15. (amended) A coextrusion blown film comprising at least one structural layer, at least one adhesive layer and optionally at least one barrier layer, the blown film obtained by a film fabrication process wherein the process time is 12 seconds or less, and wherein the adhesive composition comprises:

- a) a polyethylene selected from the group consisting of conventional-HDPE, conventional-MDPE, conventional-LLDPE, conventional-VLDPE, LDPE, and a blend of any of these five,
  - b) from 5 to 35 weight percent, based on the total weight of a) plus b) plus c), of an acid-grafted substantially linear polyethylene, c) optionally up to 30 weight percent of a hydrocarbon elastomer,
- the acid grafting agent being an unsaturated carboxylic acid or its derivative, and the level of grafting being such that the total amount of grafting agent in the total composition a) plus b) plus c) is from 0.01 to 3 weight percent.

#### REMARKS

##### About the Amendment

The amendment was made in order to independently claim a blown film obtained by a rapid fabrication process wherein the process time is 12 seconds or less. A blown film prepared by